

TECHNICAL DATA SHEET

Grade : QAMAR FC21HN

Linier low-density polyethylene

Description

This grade is an ethylene-butene copolymer produced by Eastern Petrochemical Company "SHARQ" suitable for blown film productions.

Applications

- General bag
- Industrial bag
- Food package
- Zipper bag
- Sanitary film
- Garbage bag
- Stretch film
- Heavy duty bag
- Shrink film
- Agricultural film
- Bag in box

Additive information

Slip agent : Yes, Anti-blocking agent : Yes

Nominal Resin Properties		Unit	Value	Test Method
MI (2.16kg/190°C)		g/10min.	1.0	ISO 1872-2
Density		g/cm ³	0.918	ASTM D4883
Melting point		°C	122	ISO 11357-3
Nominal Film Properties *1)		Unit	Value	Test Method
HAZE		%	11	ISO 14782
Dart Drop Impact		g	120	ISO 7765
Tensile Stress at Break	MD	MPa	55	ISO 527-3
	TD	MPa	40	
Nominal Tensile Strain at Break	MD	%	550	ISO 527-3
	TD	%	850	
Modulus of Elasticity in Tension	MD	MPa	190	ISO 527-3
	TD	MPa	220	
Elmendorf Tear Strength	MD	N/mm	30	ISO 6383-2
	TD	N/mm	160	

The information on above table shows typical properties and characteristics only and intended as guide, not as specification.

*1) Film properties were measured on 30 µm blown film produced on a 40 mm extruder, L/D 24, die width 75 mm, melt temperature 200°C, blow up ratio 2.0.

The product mentioned herein is not permitted to use medical, pharmaceutical, healthcare applications. In no event, their use for such applications shall be supported.

Disclaimer

To the best of our knowledge, the information contained herein is accurate as of the date of issue, however we do not assume any liability whatsoever for the accuracy and completeness of such information. The customer shall hold a responsibility for the decision of suitability for the customer's particular product. we assume no liability with regarding to this suitability. All IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE CLEARLY EXCLUDED. No liability can be accepted in respect of the use of SPDC's products in conjunction with other materials.

Issued by: Technical Department
Date on issue: 30/08/2022
SPDC Ref: 101.03

SPDC LTD.

2-13-10 Nagata-cho, Chiyoda-ku, TOKYO 100-0014 JAPAN
Prudential Tower 8th Floor
Phone +81-3-5156-8555, Fax +81-3-5156-8558
URL: <https://www.spdc.co.jp>

TÂN HỢP PHÚ